

LD2426K

Low Density Polyethylene Resin

Special Characteristics : InnoPlus LD2426K is produced by high pressure tubular process, a technology licensed by LyondellBasell. This grade has well balance property of optical property, mechanical property and processability.

Typical Applications : InnoPlus LD2426K is designed for variety of film application such as general purpose film, shrink film, zip bag and food packaging film. In addition, LD2426K is very suitable for liner cap, drinking water cap and vegetable oil cap.

Additives : Slip and Antiblock

Typical Properties :

Properties	InnoPlus LD2426K	Units	Test Methods
<i>Physical Properties (Based on pellets and press-molded sheet)</i>			
Melt Flow Rate at 190 °C, 2.16 kg.	4.0	g/10 min	ISO 1133
Density	0.924	g/cm ³	ISO 1183
Melting Temperature	111	°C	ISO 11357
Vicat Softening Point	93	°C	ASTM D1525
Tensile strength at Yield	11	N/mm ²	ISO 527
Tensile Modulus	260	N/mm ²	ISO 527
<i>Film Properties* (Based on blown film)</i>			
Max. Tensile Strength (MD/TD)	17 / 15	MPa	ISO 527
Ultimate Elongation (MD/TD)	300 / 540	%	ISO 527
Dart Drop Impact	100	g	ASTM D1709
Haze	< 9	%	ASTM D1003
Gloss (20°)	> 80	-	ASTM D2457
* film properties obtained from 50 microns film which was blown film extruded at blow up ratio 2.5			

Processing Condition :

Recommended melt temperature range from 150 °C to 190 °C.

Note : Properties reported here are typical values of the product, not to be considered as specifications.

PTT Global Chemical makes no representations as to the accuracy or completeness of the information contained herein.